

SPECIFYING CAVITY WALL INSULATION

This specification was prepared by
Charles E. McGuire, FCSI, CCS
Joseph J. McGuire, FCSI, CCS
Indianapolis, Indiana

March 1997

March 1997

The Dow Chemical Company

Short Form Guide Specification- Cavity Wall Insulation

STYROFOAM™ Brand CAVITYMATE™ Ultra Extruded Polystyrene Foam Insulation

PART 1 - GENERAL

1.01 RELATED DOCUMENTS

- A. Drawings and general provisions of Contract, including General and Supplementary Conditions and Division-1 Specification Sections, apply to this Section.

1.02 SUBMITTALS

- A. Manufacturer's product literature, including specified physical properties.
- B. Installation instructions.
- C. Certification that product complies with specification requirements and is suitable for the use indicated.
- D. Manufacturer's 30 Year Thermal Performance Warranty.

1.03 QUALITY ASSURANCE

- A. Cavity Wall Insulation shall not be produced with, or contain, any of the United States EPA regulated CFC Compounds listed in the Montreal Protocol of the United Nations Environmental Program.

1.04 PRODUCT HANDLING

- A. Protect insulation from physical damage.
- B. Comply with manufacturer's recommendations for handling, storage and protection.
- C. Handle boards carefully so corners are not broken off or boards otherwise damaged.

March 1997

The Dow Chemical Company

Short Form Guide Specification- Cavity Wall Insulation

STYROFOAM™ Brand CAVITYMATE™ Ultra Extruded Polystyrene Foam Insulation

1.05 WARRANTY

A. Provide written warranty that the actual thermal resistance of the extruded polystyrene foam insulation will not vary by more than 10% from its published thermal resistance.

B. Warranty period is 30 years after date insulation is purchased.

PART 2 - PRODUCTS

2.01 INSULATION

A. Material Properties:

1. Rigid closed cell extruded polystyrene foam insulation.
2. Comply with ASTM C 578-95, Type IV, density 1.6 lb/cu. ft. min., compressive resistance 25 psi (ASTM D 1621-94)
3. Thermal resistance: R-12; 5-year aged R-values of 6.0 and 5.6 min. °F-ft²-h/Btu²/inch at 40°F and 75°F respectively (ASTM C 518-91).
4. Water absorption: Max. 0.1% by volume (ASTM C 272-91(96)).
5. Surface Burning Characteristics:
 - a. Flame Spread: 15.
 - b. Smoke Developed: 165.

***Select appropriate board thickness below:

B. Thickness: nominal 1-5/8" (R-10).

or

B. Thickness: nominal 2" (R-12).

C. Acceptable manufacturer's product: The Dow Chemical Company STYROFOAM™ Brand CAVITYMATE™ Ultra Extruded Polystyrene Foam Insulation.

2.02 ADHESIVE

A. Adhesive: type recommended by insulation manufacturer.

B. Acceptable manufacturer's products:

1. ChemRex, Inc. "Contech Brands PL300 Foam Board Adhesive".
2. ChemRex, Inc. "Contech Brands Premium Foam Board Adhesive".
3. Dacar products, Inc. "Foamgrab PS".

March 1997

The Dow Chemical Company

Short Form Guide Specification- Cavity Wall Insulation

STYROFOAM™ Brand CAVITYMATE™ Ultra Extruded Polystyrene Foam Insulation

PART 3 - EXECUTION

3.01 INSPECTION AND PREPARATION

- A. Verify that masonry joints are struck flush and that other conditions are satisfactory for proper installation.
- B. Remove concrete fins and mortar projections that interfere with placement of insulation boards.

3.02 INSTALLATION

- A. Apply 2" diameter daubs of adhesive spaced approximately 12" o.c. both ways on inside face of insulation board.
- B. Butter all edges of insulation board with adhesive to provide continuous vapor barrier.
- C. Fit insulation between wall ties and other obstructions with joints staggered and edges butted tightly.
 - 1. Press units firmly against inside wythe of masonry or other construction.
 - 2. Wedge insulation from outside wythe of construction with small fragments of masonry materials spaced 24" o.c. both ways.
 - 3. Make insulation continuous. Fill all voids.

3.03 CLEAN-UP

- A. Remove and dispose of excess insulation, wrappings and other waste materials.

END OF SHORT FORM